

主な金属の物性

DOCUMENTATION

W

Mo

Ta

Ni

Ti

Al

融点
(°C)



3,410±10



2,620±10



2,990



1,453



1,941±10



680

沸点
(°C)



5,900



4,827



5,400



2,732




3,533




2,450


密度
(g/cm³)




19.21



10.19




16.65



8.902



4.507



2.7

電気抵抗
(μΩ·cm)



5.5
(20°C)




5.78
(27°C)



12.5
(18°C)



11.8



56~80



2.62